

SKF Food Grade Lubricants

# High load, water resistant and wide temperature grease

## LGFQ 2

SKF LGFQ 2 is a synthetic oil based grease using calcium suplhonate complex thickener. It is suitable for applications subjected to high loads, wet environment and fluctuating temperatures encountered in the food and beverage industry.

- Excellent corrosion protection
- · Excellent mechanical stability
- Excellent high load lubricating capacity
- Good false brinelling protection
- Good pumpability down to low temperatures
- NSF ISO 21469 registered and Halal and Kosher certified

### Typical applications

- Pellet presses (pet food, sugar, salt)
- Mixers
- Mills
- Centralized lubrication systems





Available pack sizes			
Packsize	Designation	Packsize	Designation
420 ml cartridge	LGFQ 2/0.4	Gas driven lubricators	
18 kg pail	LGFQ 2/18	LAGD series 125 ml	LAGD 125/FQ2
50 kg drum	LGFQ 2/50	Electro-mechanical lubricators	
180 kg drum	LGFQ 2/180	TLSD series 125 ml refill	LGFQ 2/SD125
		TLSD series 250 ml refill	LGFQ 2/SD250



Technical data			
Designation	LGFQ 2/(pack size)		
DIN 51825	KP1/2N-40	Corrosion protection	
Thickener	Calcium sulphonate complex	Emcor: – standard ISO 11007 – salt water test (0.5% NaCl)	0–0 0–0
NLGI grade	1–2	Water resistance	0-0
Colour	Brown	DIN 51807/1, 3 hrs at 90 °C	1 max.
Base oil type	Synthetic (PAO)	Oil separation	
Operating temperature range	−40 to +140 °C	DIN 51817, 7 days at 40 °C, %	3 max.
	(–40 to +284 °F)	Lubrication ability	
Dropping point, DIN ISO 2176	>300 °C (>570 °F)	R2F, running test B at 120 °C	Pass
Base oil viscosity		Copper corrosion	41
40 °C, mm <sup>2</sup> /s	320	DIN 51811	1b max. at 100 °C (210 °F)
100 °C, mm²/s	30	Rolling bearing grease life	1 000+120 %C (2// %F)
Penetration DIN ISO 2137	202 242	ROF test, L <sub>50</sub> life at 10 000 r/min., hrs	1 000 min. at 130 °C (266 °F)
60 strokes 100 000 strokes	280–310 +30 max.	EP performances	4
	+30 IIIdx.	DIN 51350/5, wear scar, 1 400 N, mm DIN 51350/4, weld load, N	1 max. >4 000
Mechanical stability Roll stability, 50h at 80 °C, 10-1 mm	+30 max.		
Note Stability, Solidt 60°C, 10° 111111	+30 IIIdX.	Shelf life	2 years
		NSF Reg. No.	153759



Advanced tool for grease selection and relubrication calculation

# LubeSelect for SKF greases

Selecting a suitable grease for a particular bearing is a crucial step if the bearing is to meet design expectations in its application. SKF knowledge about bearing lubrication has been encapsulated into a computer program that can be consulted at skf.com/lubeselect

LubeSelect for SKF greases provides you a user friendly tool to select the right grease and suggest frequency and quantity, while taking into account the particular conditions of your application. General guidelines for typical greases for different applications are also available.



Scan or click the QR code, or go to skf.com/lubeselect

### skf.com | skf.com/lubrication | skf.com/mapro

- ® SKF is a registered trademark of the SKF Group.
- © SKF Group 2022. All rights reserved. Please note that this publication may not be copied or distributed, in whole or in part, unless prior written permission is granted.

Every care has been taken to ensure the accuracy of the information contained in this publication, but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB MP/P8 16720/2 EN · November 2022